TERMINAL CONFIGURATIONS

Universal Terminal Terminal Height Inches (mm) 1.10 (28) Torque Values in-lb (Nm) 95-105 (11 - 12) Bolt 5/16"



MODEL: TPG12-100

VOLTAGE: 12

DIMENSIONS: Inches (mm)

BATTERY: VRLA GEL

MATERIAL: Polypropylene

WATERING SYSTEM: N/A

PRODUCT SPECIFICATIONS

BCI GROUP SIZE	ТҮРЕ	CAPACITY A Minutes	CAPACITY ^B Amp-Hours (AH)				ENERGY (kWh)	TERMINAL	DIMENSIONS ^c Inches (mm)			WEIGHT lbs.
		@25 Amps	5-Hr Rate	10-Hr Rate	20-Hr Rate	100-Hr Rate	100-Hr Rate	Type ^E	Length	Width	Height ^D	(kg)
12 VOLT DEEP CYCLE GEL BATTERY												
31	TPG12-100	200	85	94	102	108	1.30	7	12.94 (329)	6.82 (173)	9.64 (245)	70 (32)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
- The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 77°F (25°C) for Gel Lines and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
- Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.
- D. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.
- Terminal images are representative only.

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)							
System Voltage	12V	24V	36V	48V			
Absorption Charge	14.1 – 14.4	28.2 – 28.8	42.3 – 43.2	56.4 – 57.6			
Float Charge	13.5	27	40.5	54			

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

.028 VPC for every 10°F (5.55°C) above or below 77°F (25°C) (add .028 VPC for every 10°F (5.55°C) below 77°F and subtract .028 VPC for every 10°C above 77°F).

OPERATIONAL DATA


<u> </u>					
Operating Temperature	Self Discharge				
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions.				


Batteries may be utilized at higher temperatures with the understanding that battery life will be reduced by 50% for every 10° C (18° F) increase in operating temperatures over 68° F (20° C).




Trojan's battery testing procedures adhere to both BCI and IEC test standards.


BATTERY DIMENSIONS (shown with UT)







TROJAN 31-GEL PERFORMANCE



PERCENT CAPACITY VS. TEMPERATURE

